Facestock

A White, uncoated matt woodfree printing paper. Wet strength and fungicidal treatments. Made from 95% of sugar cane fibers and 5% of hemp and linen. Use of by-products from the transformation of sugar cane (bagasse).

Basis Weight 90 g/m² ISO 536 Caliper 120 µm ISO 534

Adhesive

S9500 is an acrylic based biodegradable and compostable adhesive.

Liner

BG45 white, a supercalendered glassine paper.

Basis Weight 70 g/m² ISO 536 Caliper 63 µm ISO 534 DIN 53147 Transparency 50 %

Laminate

Total Caliper 199 µm±10% ISO 534

Performance data

Initial Tack 12.5 N/25mm FTM 9 Glass FTM 2 St.St. Peel Adhesion 90° 7 N/25mm

Min. Application Temp. 5°C

-20°C to 80°C Service temperature

Adhesive Performance

The adhesive is characterized by a good initial tack and good adhesion on a wide variety of substrates.

Applications and use

This product is designed for Wine labelling, it is suitable for a large variety of sustainable labels specially in spirits.

S9500 is ideal be used for all kinds of applications, but is specifically suited for those kinds of applications where the complete packaging should be biodegradable and where indirect or direct food contact with dry foodstuff is required (ie. fruits & vegetables labeling).

Conversion & printing

Printable by all conventional printing techniques. Due to open and textured nature of the facematerial, best results are in general from those techniques with maximum conformability of printing plate such as flexo and offset. Excellent results, in line with desired image, using offset or screen.

Special Approvals

S9500 is compliant with the European food regulation 1935/2004/EC for direct food contact with dry, non-fatty foodstuff.


S9500 complies with DIN EN 13432 biodegradability and compostability regulation and is OK compost certified under the tracking number S259.

Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AM395


Fasson ® CANE FIBER PAPER WHITE - S9500-BG45WH



CANE FIBER PAPER WHITE

S9500

BG45WH



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.